



## TEST REPORT

\* **Annex A:** Staining resistance

\* **Test Method:**

ISO 26987:2008 Resilient floor coverings-Determination of staining and resistance to chemicals

\* **Test Condition:**

The main duration of contact shall be 2h. If a stain appears on the test piece after 2h, a new test shall be conducted for a period of 30 min. Examine the residual staining

\* **Test Result**

NO.	Stain agent	Contact time	Result	Contact time	Result
1	Acetone	2h	0	-	-
2	Coffee (120g coffee per litre of water)	2h	0	-	-
3	Sodium hydroxide 25% solution	2h	0	-	-
4	Hydrogen peroxide 30% solution	2h	0	-	-
	Black shoe polish	2h	0	-	-

Expression of results:

Index	Effect of test after cleaning / abrasion
0	Not affected
1	Slight
2	Moderate
3	Severe

Shaoxing Wellmark Leather CO.,LTD.  
Shaoxing Wellmark Textile CO.,LTD.