

## TEST REPORT

### 1. PVC (VINYL) FLOOR

TEST RESULTS				
TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
(UPPER)DEHP	%	-	NOT DETECTED	KS M 3802 : 2019
(UPPER)DBP	%	-	NOT DETECTED	KS M 3802 : 2019
(UPPER)BBP	%	-	NOT DETECTED	KS M 3802 : 2019
(LOWER)DEHP	%	-	0.21	KS M 3802 : 2019
(LOWER)DBP	%	-	NOT DETECTED	KS M 3802 : 2019
(LOWER)BBP	%	-	NOT DETECTED	KS M 3802 : 2019
SURFACE COATING THICKNESS (MINIMUM)	μm	-	15	KS M 3802 : 2019
SURFACE COATING THICKNESS (AVERAGE)	μm	-	15	KS M 3802 : 2019

\* METHOD DETECTION LIMIT\*

- DIETHYLHEXYL PHTHALATE (DEHP): 0.005%
- DIBUTYL PHTHALATE (DBP): 0.005%
- BUTYL BENZYL PHTHALATE (BBP): 0.005%

Shaoxing Wellmark Leather CO.,LTD.  
Shaoxing Wellmark Textile CO.,LTD.